

HYDRO SEALING TECHNOLOGY SDN BHD (426172-P)

(Sales Tax ID No : J31-1808-21018370)

No.5, Jalan Tiong Emas 4, Kawasan Perindustrian Tiong Nam,
81100, Johor Bahru, Johor, Malaysia.

Tel : 07 - 3620022 Fax : 07 - 350 7319

Email : sales@hydro.com.my

Website : www.hydro.com.my

HYDRO
House of Seals

Material Safety Data Sheet

RUBBER - EPDM

General Information

EPDM is based on ethylene-propylene rubber. It has outstanding resistance to hot water, steam, washing agents and polar organic solvents and good resistance to weathering, ozone and ageing. EPDM is not resistant to mineral, vegetable and animal oils.

Physical Properties

Colour :			black
Hardness at 20° :	DIN 53505	Shore A	85 +/- 2
Density :	DIN 53479	g/cm ³	1.23
100% Modulus :	DIN 53504	N/mm ²	> 10
300% Modulus :	DIN 53504	N/mm ²	
Tensile Strength :	DIN 53504	N/mm ²	> 14
Elongation at break :	DIN 53504	%	> 130
Rebound resilience :	DIN 53512	%	> 38
Tear Strength :	DIN 53515	N/mm ²	> 15
Abrasion :	DIN 53516	mm ³	<120
Compression set :**	DIN 53517	%	< 15
Min. service temperature :		°C	-50
Max. service temperature :		°C	150

* Compression set : 100°C, 22 hours.

Remark

All test methods and values mentioned above are corresponding to ASTM or DIN standards and have been tested on standardized plates in the laboratory. All tests are made under laboratory conditions.