

HYDRO SEALING TECHNOLOGY SDN BHD (426172-P)

(Sales Tax ID No : J31-1808-21018370)

No.5, Jalan Tiong Emas 4, Kawasan Perindustrian Tiong Nam,
81100, Johor Bahru, Johor, Malaysia.

Tel : 07 - 3620022 Fax : 07 - 350 7319

Email : sales@hydro.com.my

Website : www.hydro.com.my

HYDRO
House of Seals

Material Safety Data Sheet

HPU

General Information

HPU is a MDI based polyurethane system which has been specially modified and developed for sealing applications. HPU has been optimized in regards to hydrolysis stability and mechanical properties. It has high tensile strength, very high abrasion resistance, low hysteresis, very good flexibility at low temperatures (-30/-40°C) and low compression-set.

Physical Properties

Colour :			red
Hardness at 20° :	DIN 53505	Shore A	95 +/- 2
Density :	DIN 53479	g/cm ³	1.17
100% Modulus :	DIN 53504	N/mm ²	>14
300% Modulus :	DIN 53504	N/mm ²	>33
Tensile Strength :	DIN 53504	N/mm ²	>55
Elongation at break :	DIN 53504	%	>430
Rebound resilience :	DIN 53512	%	>49
Tear Strength :	DIN 53515	N/mm ²	>125
Abrasion :	DIN 53516	mm ³	<15
Compression set :**	DIN 53517	%	<21
Min. service temperature :		°C	-35
Max. service temperature :		°C	110

* Compression set : 70°C, 23 hours, 25% deflexion.

Remark

All test methods and values mentioned above are corresponding to ASTM or DIN standards and have been tested on standardized plates in the laboratory. All tests are made under laboratory conditions.